

УДК 621.762; 537.523.4

# Износостойкость Ti-Mo-Si покрытий, формируемых методом электроискрового легирования на титановом сплаве Ti-6Al-4V

А.А. Бурков<sup>1</sup>, М.А. Кулик<sup>1</sup>, А.Ю. Бычуря<sup>1</sup>, В.О. Круткова<sup>2</sup>

<sup>1</sup>Хабаровский Федеральный исследовательский центр ДВО РАН,  
ул. Тихоокеанская, 153, г. Хабаровск 680042, Россия

<sup>2</sup>Институт тектоники и геофизики им. Ю.А. Косыгина ДВО РАН,  
г. Хабаровск, Россия

Поступила в редакцию 01.08.2024.

После доработки 05.02.2025.

Принята к публикации 14.02.2025.

Исследовались Ti-Mo-Si покрытия для защиты титанового сплава Ti-6Al-4V от изнашивания и высокотемпературного окисления нанесённые методом электроискрового легирования. Для формирования Ti-Mo-Si покрытия использовался нелокализованный электрод, состоящий из титановых гранул с добавлением порошков кремния и молибдена. Для изучения фазового состава покрытий применяли рентгеновский дифрактометр Дрон-7 в  $\text{Cu}K_{\alpha}$  излучении. Согласно данным рентгенофазового анализа в составе покрытий обнаружены фазы  $\alpha\text{Ti}$ , Mo,  $\text{Ti}_5\text{Si}_3$  и  $\text{TiSi}_2$ . Средняя толщина, приготовленный покрытий, находилась в диапазоне от 31,70 до 40,97 мкм. По данным энергодисперсионного анализа в составе покрытий преобладал титан, концентрация молибдена достигала 18 ат. %, а кремния — 9 ат. %. Показано, что частицы кремния непропорционально меньше участвовали в формировании покрытия по сравнению с частицами молибдена. Испытание на жаростойкость показало, что применение разработанных Ti-Mo-Si покрытий позволяет повысить жаростойкость титанового сплава Ti-6Al-4V при температуре 900 °C до 5,7 раза. Микротвёрдость поверхности Ti-Mo-Si покрытий находилась в диапазоне от 5,81 до 9,88 ГПа. Установлено, что с ростом соотношения кремния к молибдену в нелокализованном электроде, средние значения коэффициента трения покрытий в режиме сухого скольжения монотонно повышались от 0,81 до 0,86. Применение Ti-Mo-Si покрытий позволяет снизить износ поверхности изделий из титанового сплава до 19 раз. Наибольшую твёрдость, износостойкость и жаростойкость продемонстрировало покрытие с наибольшим содержанием кремния.

**Ключевые слова:** Ti-Mo-Si покрытие, электроискровое легирование, износ, жаростойкость, твердость, сплав Ti-6Al-4V.

**DOI:** 10.32864/0202-4977-2025-46-1-15-25

---

**Адрес для переписки:**

М.А. Кулик  
Хабаровский Федеральный исследовательский центр ДВО РАН,  
ул. Тихоокеанская, 153, г. Хабаровск 680042, Россия  
e-mail: marijka80@mail.ru

**Для цитирования:**

А.А. Бурков, М.А. Кулик, А.Ю. Бычуря, В.О. Круткова.  
Износостойкость Ti-Mo-Si покрытий, формируемых методом  
электроискрового легирования на титановом сплаве Ti-6Al-4V.  
Трение и износ.  
2025. — Т. 46, № 1. — С. 15—25.  
DOI: 10.32864/0202-4977-2025-46-1-15-25

**Address for correspondence:**

M.A. Kulik  
Khabarovsk Federal Research Center FEB RAS,  
Tikhookeanskaya Str., 153, Khabarovsk 680042, Russia  
e-mail: marijka80@mail.ru

**For citation:**

A.A. Burkov, M.A. Kulik, A.Y. Bytsura, and V.O. Krutikova.  
[Wear Resistance of Ti-Mo-Si Coatings Formed by Electrosparck  
Alloying on Titanium Alloy Ti-6Al-4V].  
Trenie i Iznos.  
2025, vol. 46, no. 1, pp. 15–25 (in Russian).  
DOI: 10.32864/0202-4977-2025-46-1-15-25

# Wear Resistance of Ti-Mo-Si Coatings Formed by Electrospark Alloying on Titanium Alloy Ti-6Al-4V

A.A. Burkov<sup>1</sup>, M.A. Kulik<sup>1</sup>, A.Y. Bytsura<sup>1</sup>, and V.O. Krutikova<sup>2</sup>

<sup>1</sup>Khabarovsk Federal Research Center FEB RAS,  
Tikhookeanskaya Str., 153, Khabarovsk 680042, Russia

<sup>2</sup>Institute of Tectonics and Geophysics, Far Eastern Branch of the Russian Academy of Sciences,  
Khabarovsk, Russia

Received 01.08.2024.

Revised 05.02.2025.

Accepted 14.02.2025.

## Abstract

Ti-Mo-Si coatings were prepared to protect of the titanium alloy Ti-6Al-4V from wear and high-temperature oxidation by the electrospark deposition method was investigated. To form the Ti-Mo-Si coating, a non-localized electrode consisting of titanium granules with the addition of silicon and molybdenum powders was used. The aim of the work is to study the influence of the silicon and molybdenum ratio in the non-localized electrode on the character of mass transfer during the electrospark deposition Ti-Mo-Si coatings, their composition, microstructure, oxidation resistance and tribological properties. To study the phase composition of the coatings, a Dron-7 X-ray diffractometer in  $\text{Cu}K\alpha$  radiation was used. According to the X-ray phase analysis data, the phases of  $\alpha\text{Ti}$ , Mo,  $\text{Ti}_5\text{Si}_3$  and  $\text{TiSi}_2$  were found in the composition of the coatings. The average thickness of the prepared coatings was in the range from 31.70 to 40.97  $\mu\text{m}$ . According to the energy-dispersive analysis data, titanium predominated in the composition of the coatings, the molybdenum concentration reached 18 at. %, and silicon — 9 at. %. It is shown that silicon particles participated disproportionately less in the coating formation compared to molybdenum particles. Oxidation resistance testing showed that the use of the developed Ti-Mo-Si coatings allows increasing the high temperature oxidation resistance of the titanium alloy Ti-6Al-4V at a temperature of 900 °C by up to 5.7 times. The microhardness of the Ti-Mo-Si coating surface was in the range from 5.81 to 9.88 GPa. It was found that with an increase in the silicon to molybdenum ratio in the non-localized electrode, the average values of the friction coefficient of the coatings in the dry sliding mode monotonically increased from 0.81 to 0.86. The use of Ti-Mo-Si coatings allows reducing the surface wear of titanium alloy products by up to 19 times. The highest hardness, wear resistance and oxidation resistance were demonstrated by the coating with the highest silicon content.

**Keywords:** coating Ti-Mo-Si, electric spark deposition, wear, oxidation resistance, hardness, Ti-6Al-4V.

**DOI:** 10.32864/0202-4977-2025-46-1-15-25

---

### Адрес для переписки:

М.А. Кулік  
Хабаровський Федеральний іншледовательський центр ДВО РАН,  
ул. Тихоокеанская, 153, г. Хабаровск 680042, Россия  
e-mail: marijka80@mail.ru

### Для цитирования:

А.А. Бурков, М.А. Кулік, А.Ю. Быцюра, В.О. Крутікова.  
Ізносостойкость Ti-Mo-Si покрытий, формируемых методом  
электроискрового легирования на титановом сплаве Ti-6Al-4V.  
Трение и износ.  
2025. — Т. 46, № 1. — С. 15—25.  
DOI: 10.32864/0202-4977-2025-46-1-15-25

---

### Address for correspondence:

M.A. Kulik  
Khabarovsk Federal Research Center FEB RAS,  
Tikhookeanskaya Str., 153, Khabarovsk 680042, Russia  
e-mail: marijka80@mail.ru

### For citation:

A.A. Burkov, M.A. Kulik, A.Y. Bytsura, and V.O. Krutikova.  
[Wear Resistance of Ti-Mo-Si Coatings Formed by Electrospark  
Alloying on Titanium Alloy Ti-6Al-4V].  
*Trenie i Iznos*.  
2025, vol. 46, no. 1, pp. 15—25 (in Russian).  
DOI: 10.32864/0202-4977-2025-46-1-15-25

## Список использованных источников

1. Dai J., Zhu J.Y., Chen C.Z. [et al.]. High Temperature Oxidation Behavior and Research Status of Modifications on Improving High Temperature Oxidation Resistance of Titanium Alloys and Titanium Aluminides: A Review // Journal of Alloys and Compounds. — 2016 (685), 784—798
2. Shafyei H., Salehi M., and Bahrami A. Fabrication, Microstructural Characterization and Mechanical Properties Evaluation of Ti/TiB/TiB<sub>2</sub> Composite Coatings Deposited on Ti6Al4V Alloy by Electro-Spark Deposition Method // Ceramics International. — 2020 (46), 15276—15284
3. Кудряшов А.Е., Замулаева Е.И., Кирюханцев-Корнеев Ф.В. [и др.] Особенности формирования на хромовой подложке электроискровых покрытий при использовании керамических электродов ZrSi<sub>2</sub>-MoSi<sub>2</sub>-ZrB<sub>2</sub> и HfSi<sub>2</sub>-MoSi<sub>2</sub>-HfB<sub>2</sub> // Электронная обработка материалов. — 2024, № 3, 1—12
4. Lu Q., Hao Y., Wang Y. [et al.] Microstructural Evolution and High-Temperature Oxidation Mechanisms of a Ti-Mo-Si Composite // Corrosion Science. — 2019 (161), 108180
5. El-Sayed Seleman M.M., Ataya S., Aly H.A. [et al.] Effect of the Si Content on the Dry and Wet Sliding Wear Behavior of the Developed Ti-15Mo-(0-2) Si Alloys for Biomedical Applications // Metals. — 2023 (13), no. 11, 1861
6. Li C., Zhan Y., Mo Y., [et al.] In situ Synthesized Ti<sub>5</sub>Si<sub>3</sub>/Ti-Mo Lightweight Structural Composites // International Journal of Refractory Metals and Hard Materials. — 2013 (41), 432—436
7. Li F., Zhang P., Wei D. [et al.] The Influence of Loading Rate and Hold Time on the Nano-Mechanical Properties of  $\gamma$ -TiAl and Plasma Mo-Si-Ti Coating // Journal of Materials Engineering and Performance. — 2022 (31), no. 9, 7368—7381
8. Li L., Guo X., and Qiao Y. A Novel Composite Si-Mo-Ti Coating with Ti Concentration Gradient for Nb-Si Based Ultrahigh Temperature Alloy Prepared by Slurry Sintering // Corrosion Science. — 2023 (225), 111632
9. Верхутуров А.Д., Подчерняева И.А., Панашенко В.М., Коневцов Л.А. Электроискровое легирование титана и его сплавов металлами и композиционными материалами. — Комсомольск на Амуре. — 2014
10. Николенко С.В., Сюй Н.А., Пугачевский М.А., Метлицкая Л.П. Создание безвольфрамовых электродов СВС-экструзией для электроискрового легирования стали 45 // Вестник машиностроения. — 2013, № 2, 37—42
11. Бурков А.А., Кулик М.А., Быцтура А.Ю., Ермаков М.А. Осаждение износостойкого Cr-Fe-Al<sub>2</sub>O<sub>3</sub> покрытия на сталь 35 с использованием порошка оксида алюминия // Трение и износ. — 2023 (44), № 6, 521—531
12. Burkov A.A., Chigrin P.G., and Dvornik M.I. Electrosparc CuTi Coatings on Titanium Alloy Ti6AL4V: Corrosion and Wear Properties // Surface and Coatings Technology. — 2023 (469), 129796
13. Litvinov E.A., Mesyats G.A., and Proskurovskii D.I. Field Emission and Explosive Electron Emission Processes in Vacuum Discharges // Soviet Physics Uspekhi. — 1983 (26), no. 2, 138
14. Бурков А.А., Кулик М.А., Круткова В.О. Характеристика Ti-Si-покрытий на сплаве Ti6AL4V, осажденных электроискровой обработкой в среде гранул // Цветные металлы. — 2019 (4), 54—59
15. Li F., Rawat R.S., Zhang P. [et al.] Mechanical Properties and Reciprocating Sliding Tribological Behaviors of  $\gamma$ -TiAl Substrate and Plasma-Based Mo-Si-Ti Coating // Journal of Materials Research and Technology. — 2023 (26), 1469—1483

## References

1. Dai J., Zhu J.Y., Chen C.Z. [et al.]. High Temperature Oxidation Behavior and Research Status of Modifications on Improving High Temperature Oxidation Resistance of Titanium Alloys and Titanium Aluminides: A Review // Journal of Alloys and Compounds. — 2016 (685), 784—798
2. Shafyei H., Salehi M., and Bahrami A. Fabrication, Microstructural Characterization and Mechanical Properties Evaluation of Ti/TiB/TiB<sub>2</sub> Composite Coatings Deposited on Ti6Al4V Alloy by Electro-Spark Deposition Method // Ceramics International. — 2020 (46), 15276—15284
3. Kudryashov A.E., Zamulaeva E.I., Kiryukhantsev-Korneev F.V. [et al.] Features of the formation of electrospark coatings on a chromium substrate using ceramic electrodes ZrSi<sub>2</sub>-MoSi<sub>2</sub>-ZrB<sub>2</sub> and HfSi<sub>2</sub>-MoSi<sub>2</sub>-HfB<sub>2</sub> // Electronic processing of materials. — 2024, no. 3, 1—12 (in Russian)
4. Lu Q., Hao Y., Wang Y. [et al.] Microstructural Evolution and High-Temperature Oxidation Mechanisms of a Ti-Mo-Si Composite // Corrosion Science. — 2019 (161), 108180
5. El-Sayed Seleman M.M., Ataya S., Aly H.A. [et al.] Effect of the Si Content on the Dry and Wet Sliding Wear Behavior of the Developed Ti-15Mo-(0-2) Si Alloys for Biomedical Applications // Metals. — 2023 (13), no. 11, 1861
6. Li C., Zhan Y., Mo Y., [et al.] In situ Synthesized Ti<sub>5</sub>Si<sub>3</sub>/Ti-Mo Lightweight Structural Composites // International Journal of Refractory Metals and Hard Materials. — 2013 (41), 432—436
7. Li F., Zhang P., Wei D. [et al.] The Influence of Loading Rate and Hold Time on the Nano-Mechanical Properties of  $\gamma$ -TiAl and Plasma Mo-Si-Ti Coating // Journal of Materials Engineering and Performance. — 2022 (31), no. 9, 7368—7381
8. Li L., Guo X., and Qiao Y. A Novel Composite Si-Mo-Ti Coating with Ti Concentration Gradient for

- Nb-Si Based Ultrahigh Temperature Alloy Prepared by Slurry Sintering // Corrosion Science. — 2023 (225), 111632
9. Verkhoturov A.D., Podchernyaeva I.A., Panashenko V.M., Konevtsov L.A. Electrospar deposition of titanium and its alloys with metals and composite materials. — Komsomolsk-on-Amur. — 2014 (in Russian)
10. Nikolenko R.R., Syui N.A., Pugachevskyi M.A., Metlitskaya L.P. The development of non-tungsten electrodes by SHS extrusion for electrospar deposition addition of medium alloy steel // Bulletin of mechanical engineering. — 2013, № 2, 37—42 (in Russian)
11. Burkov A.A., Kulik M.A., Bytsura A.Y., and Er-makov M.A. Wear-Resistant Cr-Fe-Al<sub>2</sub>O<sub>3</sub> Coating Deposition on Steel 35 Using Aluminum Oxide Powder // Journal of Friction and Wear. — 2023 (44), no. 6, 346—353
12. Burkov A.A., Chigrin P.G., and Dvornik M.I. Electrospar CuTi Coatings on Titanium Alloy Ti6Al4V: Corrosion and Wear Properties // Surface and Coatings Technology. — 2023 (469), 129796
13. Litvinov E.A., Mesyats G.A., and Proskurovskii D.I. Field Emission and Explosive Electron Emission Processes in Vacuum Discharges // Soviet Physics Uspekhi. — 1983 (26), no. 2, 138
14. Burkov A.A., Kulik M.A., Krutikova V.O. Characteristics of Ti-Si Coatings on Ti6Al4V Alloy Subjected to Electrospar Granules Deposition // Tsvetnye Metally. — 2019 (4), 54—59 (in Russian)
15. Li F., Rawat R.S., Zhang P. [et al.] Mechanical Properties and Reciprocating Sliding Tribological Behaviors of γ-TiAl Substrate and Plasma-Based Mo-Si-Ti Coating // Journal of Materials Research and Technology. — 2023 (26), 1469—1483

Для приобретения полного текста статьи, обращайтесь в редакцию журнала.  
Адрес редакции: 246050, ул. Кирова 32а, г. Гомель, Belarus. Телефон/факс: +375 (232) 34 06 36 / 34 17 11  
*Full text of articles can be purchased from the editorial office.*  
*Address: 32a Kirov Street, Gomel, Belarus, 246050. Phone: +375 (232) 34 06 36. Fax: +375 (232) 34 17 11*  
E-mail: [FWJ@tut.by](mailto:FWJ@tut.by)